

See discussions, stats, and author profiles for this publication at: <https://www.researchgate.net/publication/348886963>

Facile fabrication of nitrogen-doped Titanium dioxide- based dye-sensitized solar cells

Conference Paper · January 2021

CITATIONS

0

READS

59

5 authors, including:



Vijayakumar Gurunathanan

University of Jaffna

3 PUBLICATIONS 1 CITATION

[SEE PROFILE](#)



Tharmakularasa Rajaramanan

University of Jaffna

8 PUBLICATIONS 9 CITATIONS

[SEE PROFILE](#)



Punniamoorthy Ravirajan

University of Jaffna

91 PUBLICATIONS 2,171 CITATIONS

[SEE PROFILE](#)



Dhayalan Velauthapillai

Høgskulen på Vestlandet

250 PUBLICATIONS 2,000 CITATIONS

[SEE PROFILE](#)

Some of the authors of this publication are also working on these related projects:



Focusing of electromagnetic waves into a dielectric slab [View project](#)



CBERC and HRNCET projects [View project](#)

Conference Abstract

Facile fabrication of nitrogen-doped Titanium dioxide-based dye-sensitized solar cells

V. Gurunathanan¹, T. Rajaramanan^{1,2,3}, D. Velauthapillai³, P. Ravirajan^{1*} and M. Senthilnathanan²

¹ Department of Physics, Faculty of Science, University of Jaffna, Jaffna 40000, Sri Lanka

² Department of Chemistry, University of Jaffna, Jaffna 40000, Sri Lanka

³ Faculty of Engineering and Science, Western Norway University of Applied Sciences, Norway
pravirajan@univ.jfn.ac.lk*

Abstract

Titanium dioxide (TiO₂) is a commonly used semiconductor in Dye-Sensitized Solar cells (DSSCs) as it is inexpensive, abundant and innocuous to the environment. However, lack of response to the visible light and slow electron mobility limit its performance. Doping TiO₂ with a non-metal such as Nitrogen has been found to improve light absorption in the visible region of the solar spectrum and also enhance the charge transport in the DSSCs[1],[2]. This study reports a facile method to fabricate the nitrogen-doped TiO₂ photoanode. A series of nitrogen-doped TiO₂ films were prepared by grinding TiO₂ with various amount of NH₄OH and followed by calcination at 500°C. These films were characterized by X-ray diffraction (XRD) and UV-Visible spectroscopy, which confirmed an increase in particle size and red shift in the spectrum by nitrogen-doping respectively. Finally, the photovoltaic devices were fabricated using N719 dye, I⁻/I₃⁻ electrolyte and Pt counter electrode and device performance was tested under simulated irradiation of intensity 100 mW/cm² with AM 1.5 filter. 20% enhancement in Power Conversion Efficiency (PCE) was observed for the optimized Nitrogen-doped TiO₂ based device compared to the control device. Moreover, doping TiO₂ using Nitrogen enhanced the short circuit current density (J_{SC}) from 11.9 to 13.7 mA/cm². The improvement in J_{SC} is attributed to the reduced charge transport resistance which was confirmed by the Electrochemical Impedance Spectroscopy (EIS).

Keywords: Dye sensitized solar cell, Photo anode, Doping, TiO₂

Acknowledgement: This work was supported by Norwegian Agency for International Cooperation and Quality Enhancement in Higher Education (DIKU) and Norwegian Embassy in Colombo under the research grant NORPART 2016/10237

References

- [1] S. H. Kang, et.al., Mater. Chem. Phys., (2010), **124** (1), 422-42
- [2] W. Guo, et.al., Electrochim. Acta, (2011), **56** (12), 4611-4617